

Naam	Droogkrimp (%)	Stooktemp (°C)	Water opname (%)						Stookkrimp (%)						Kleur	Chamotte		Opmerkingen
			1000°C	1040°C	1100°C	1140°C	1200°C	1260°C	1000°C	1040°C	1100°C	1140°C	1200°C	1260°C		%	korrel (mm)	
K120	5,0	1000 - 1150	11	-	8	-	-	-	1,5	-	3	-	-	-	gemarmerd	25	0 - 0,5	
K123	5,0	1000 - 1280	-	10	8	7	4	2,5	-	1	2	3,5	4,5	4,5	wit	25	0 - 0,5	
K125	6,2	1000 - 1250	-	8,5	5,4	4	1,5	-	-	3,2	4,4	5	5,8	-	rood	25	0 - 0,5	
K126	5,5	1000 - 1120	-	-	6	-	-	-	-	-	4,8	-	-	-	terracotta	25	0 - 0,5	aangekleurd met ijzeroxide
K127	5,0	1000 - 1140	9,5	7	3	2	-	-	2	4	5,5	6,5	-	-	bruin-zwart	25	0 - 0,5	
K129	5,5	1000 - 1280	-	-	-	-	7,5	4	-	-	-	-	5	6	wit	30	0 - 0,5	met molochiet; voor raku
K130	5,5	1000 - 1280	-	-	-	-	4	-	-	-	-	-	4	-	wit	25	0 - 0,5	
K132	5,8	1000 - 1250	12	-	10	-	4,5	-	2	-	4,5	-	5	-	rood	25	0,5 - 2,0	
K134	5,0	1000 - 1200	11	-	5	-	2	-	2	-	5,5	-	6	-	bruin-zwart	25	0,5 - 2,0	
K140	5,5	1000 - 1150	17	15	13	-	-	-	0,2	0,3	0,4	-	-	-	extra wit	-	-	giet-equivalent: WB30PM
K142	6,0	1000 - 1150	17	15	15	15	-	-	0,2	0,5	1,8	2	-	-	rood	-	-	
K143	5,5	1000 - 1150	-	9	-	-	-	-	-	2	-	-	-	-	terracotta	-	-	aangekleurd met ijzeroxide
K144	5,8	1000 - 1150	-	9	6	-	-	-	-	3,5	3	-	-	-	bruin-zwart	-	-	
K146	4,5	1000 - 1260	-	-	-	-	2	-	-	-	-	-	5,5	-	wit	-	-	
K147	5,5	1000 - 1150	13	12	-	-	-	-	0,2	0,2	0,3	-	-	-	wit	-	-	
K3020	4,5	1000 - 1200	11	-	7	-	-	-	1	-	4	-	-	-	kurk	30	0 - 1,0	met zwarte chamotte
Raku5015	4,5	1000 - 1280	-	-	8	-	6	3,5	-	-	2	-	3,5	5	wit	50	0 - 1,5	voor raku
RTM3010	5,5	1000 - 1280	11	-	5	-	2	-	1	-	4	-	5	-	rose/geel/crème	30	0 - 1,0	
RTM5015	5,0	1000 - 1280	12	-	9	-	6	-	1	-	2	-	3,5	-	rose/geel/crème	50	0 - 1,5	
Terrazo Blue	5,8	1000 - 1280	-	-	13	-	6	3	-	-	2	-	5	6	blauw	40	0 - 2,0	
Terrazo Umbra	6,0	1000 - 1280	-	-	10	-	4	3	-	-	3	-	6	6,5	umber	40	0 - 2,0	
Terrazo Yellow	6,5	1000 - 1280	-	-	8	-	4,5	4	-	-	3	-	4,5	5	geel	40	0 - 2,0	
WB01795	5,0	1000 - 1300	-	-	-	-	4,5	2	-	-	-	-	5	6	wit	40	0 - 2,0	